

DUPONT™ SOLAMET® PV410

TECHNICAL DATA SHEET

PRODUCT DESCRIPTION

DuPont™ Solamet® PV410 photovoltaic metallization silver conductor is used to provide front side connectivity for thin film based photovoltaic cells. It was designed to provide good contact resistance to transparent conductive oxides (TCO's).

PRODUCT BENEFITS

- Good contact resistance to TCO's
- Excellent adhesion to sputtered ZnO
- Excellent conductivity
- Fine line print capability
- Good printability

PROCESSING SUMMARY

- **Screen Printing Equipment**
Reel-to-reel, semi-automatic, manual
- **Substrate**
Rigid/Flexible with sputtered/coated TCO
- **Screen Type**
PET or Stainless Steel (325 mesh)
- **Typical Drying Conditions**
Substrate/cell dependent, 130–170°C/5–60 min
- **Typical Circuit Line Thickness**
12 µm for a track width around 150 µm (using a 325 mesh SS screen, 12 µm emulsion)
- **Clean up Solvent**
Ethylene Glycol diacetate

TABLE 1 – TYPICAL COMPOSITION AND PHYSICAL PROPERTIES

Test	Properties
Solids (%) at 750°C	78–80
Viscosity (Pa·s) (Brookfield RVT, spindle #14, 10rpm)	30–55
Thinner	8210
Resistivity (mΩ/sq/25µm)	≤18
Coverage, cm ² /g	120–150
Abrasion Resistance (ASTM Pencil Hardness)	2H
Solderability	Not Recommended

PASTE PREPARATION

The composition should be thoroughly mixed before use. This is best achieved by slow, gentle hand stirring with a clean burr-free spatula (flexible plastic) for 1–2 minutes. Jar rolling is NOT recommended, as this could change the rheology of the material. Care should be taken to avoid air entrapment.

DRYING

Depending on the temperature tolerance of the cell and substrate, Solamet® PV410 can be dried at temperatures between 130°C and 170°C. Drying times can vary depending on the efficiency of the dryer. Longer drying times and higher drying temperatures will improve the adhesion, resistivity and abrasion resistance.

PRINTING

Printing should be carried out in a clean, well-ventilated area. DuPont™ Solamet® PV410 photovoltaic composition, in its container, should be at ambient temperature prior to commencement of printing.

THINNER

This composition is optimized for screen printing, thinning is not normally required. Use the DuPont recommended thinner for slight adjustments to viscosity or to replace evaporation losses. The use of too much thinner or the use of a non recommended thinner may affect the rheological behavior of the material and its printing characteristics. Refer to the table.

All values reported here are results of experiments in our laboratories intended to illustrate product performance potential with a given experimental design. They are not intended to represent the product's specifications, details of which are available upon demand.

DUPONT™ SOLAMET® PV410

TECHNICAL DATA SHEET


STORAGE AND SHELF LIFE

Containers may be stored in a clean, stable environment at room temperature (between 5°C–30°C), with their lids tightly sealed. Storage in high temperature (>30°C) or in freezers (temperature < 0°C) is NOT recommended as this could cause irreversible changes in the material. The shelf life of compositions in factory-sealed (unopened) containers between (5°C–30°C) conditions is 6 months from date of shipment.

SAFETY AND HANDLING

For information on health and safety regulations please refer to the specific product MSDS.

FIGURE 1 – 85°C/85% RH STABILITY



For more information on DuPont™ Solamet® PV410 photovoltaic metallization or other DuPont Microcircuit Materials, please contact your local representative:

Americas

DuPont Microcircuit Materials
14 TW Alexander Drive
Research Triangle Park, NC 27709 USA
Tel +1 800 284 3382 (calls within USA)
Tel +1 919 248 5188 (calls outside USA)

DuPont Taiwan Limited
45, Hsing-pont Road
Taoyuan, 330 Taiwan
Tel +886 3 377 3616

E.I. DuPont India Private Limited
7th Floor, Tower C, DLF Cyber Greens
Sector-25A, DLF City, Phase-III
Gurgaon 122 002 Haryana, India
Tel +91 124 409 1818

Europe, Middle East & Africa

Du Pont (UK) Ltd
Coldharbour Lane
Bristol BS16 1QD UK
Tel +44 117 931 3191

DuPont China Holding Company
Ltd
Bldg. 11, 399 Keyuan Road
Zhangjiang Hi-Tech Park
Pudong New District
Shanghai 201203
Tel +86 21 6386 6366 ext. 2202

Du Pont Company (Singapore) Pte Ltd
1 HarbourFront Place, #11-01
HarbourFront Tower One
Singapore 098633
Tel +65 6586 3022

Asia

Du Pont Kubushiki Kaisha
Sanno Park Tower, 11-1
Nagata-cho, 2-chome
Chiyoda-ku, Tokyo, 100-611 Japan
Tel +81 3 5521 8650

DuPont Korea Inc.
3-5th Floor, Asia tower #726
Yeoksam-dong, Gangnam-gu
Seoul 135-719, Korea
Tel +82 10 6385 5399

<http://mcm.dupont.com>
<http://photovoltaics.dupont.com>

Copyright © 2014 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, and all DuPont products denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-3 ("Medical Applications Policy") and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-3 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user's consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data's accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user's responsibility to satisfy itself that the product is suitable for the user's intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws. This information may be subject to revision as new knowledge and experience become available.

This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.