

DUPONT™ SOLAMET® PV52A

TECHNICAL DATA SHEET

PRODUCT DESCRIPTION

DuPont™ Solamet® PV52A photovoltaic metallization back side paste is a highly conductive solderable silver composition, developed to lower consumption yet providing excellent adhesion when used in conjunction with back side aluminum compositions. This paste may be co-fired with front side (n-type) silver conductors such as DuPont™ Solamet® PV17x, PV18x and with back side (p-type) aluminum conductors such as DuPont™ Solamet® PV3xx.

PRODUCT BENEFIT

- Excellent solderability
- High adhesion with ultra low consumption
- High conductivity
- Compatible with back side Al metallizations
- Co-fireable with front side silver and back side aluminum
- Good printing characteristics
- Lead and cadmium free*

*Cadmium 'free' as used herein means that cadmium is not an intentional ingredient in and is not intentionally added to the referenced product. Trace amounts however may be present.

PROCESSING SUMMARY

- **Application**
Standard screen print process
- **Printing**
Speed 6–8 in/sec (150–250 mm/sec)
- **Drying**
Vertical Dryer 170 – 230°C 10 minutes
Vertical Dryer 170–230°C 10 minutes
IR Belt Dryer 220–270°C 30 seconds
Flexible in accordance with industry practice. Actual settings to be determined by dryer type
- **Screen Type**
150–280 mesh stainless steel with 5–15 µm emulsion
- **Typical Line Thickness**
3–5µm
- **Soldering**
Compatible with industry standard material and condition
Flux type: non-clean, reactivity level L0/M0 (Standard: ANSI/J-STD-004)
Ribbon: compatible with Pb contained and Pb free solder material, i.e. 60Sn/40Pb, 62Sn/36Pb/2Ag, 96.5Sn/3.5Ag

TABLE 1: TYPICAL PHYSICAL PROPERTIES

Viscosity (Pa·s) (Brookfield HADV, SC4-14/6R @ 10 rpm, 25°C))	50–100
Solids (%) at 750°C	43–45
Fineness of Grind (4 th /50%)	<12µm/<6µm
Thinner	9450
Shelf Life (months)	6

PASTE PREPARATION

The composition should be thoroughly mixed before use. This is best achieved by slow, gentle hand stirring with a clean burr-free spatula (flexible plastic) for 0.5–1 minutes. Jar rolling is NOT recommended, as this could change the rheology of the material. Care should be taken to avoid air entrapment.

PRINTING

Printing should be carried out in a clean, well-ventilated area. DuPont™ Solamet® PV52A photovoltaic composition, in its container, should be at ambient temperature prior to commencement of printing.

FIRING

Solamet® PV52A is designed for rapid (spike) firing. Thermal budget above 600°C should be kept to minimum, ideally <8 seconds to ensure optimum electrical contact to the wafer. See Chart 1 for typical firing profile. Actual furnace settings and belt speed will depend on the wafer thickness, texturing and emitter resistivity as these influence the temperature of the wafer during firing.

It is important that wafers are fired in a well ventilated furnace, with a continuous supply of clean filtered air.

Airflow and extraction rates should be optimized to ensure that oxidizing conditions exist within the furnace firing chamber, especially when front and backside conductors are co-fired.



DUPONT™ SOLAMET® PV52A

TECHNICAL DATA SHEET

THINNER

Solamet® PV52A composition is optimized for screen printing and thinning is not normally required. Use the DuPont recommended thinner for slight adjustments to viscosity or to replace evaporation losses. The use of too much thinner or the use of a non recommended thinner may affect the rheological behavior of the material and its printing characteristics. Please refer to Table 1.


STORAGE

Containers may be stored in a clean, stable environment at room temperature (between 5°C–25°C) with their lids tightly sealed. Storage in high temperature (>30°C) or in freezers (temperature <0°C) is NOT recommended as this could cause irreversible changes in the material.

SAFETY AND HANDLING

For information on health and safety regulations please refer to the specific product MSDS.

CHART 1
TYPICAL FIRING PROFILE



For more information on DuPont™ Solamet® PV52A or other DuPont Microcircuit Materials products, please contact your local representative:

Americas

DuPont Microcircuit Materials
14 T.W. Alexander Drive
Research Triangle Park, NC 27709
USA
Tel. +1800 284-3382 (calls within USA)
Tel. +1919 248 5188 (calls outside USA)

DuPont Taiwan Ltd
45, Hsing-Pont Road,
Taoyuan, 330
Taiwan
Tel. +886-3-377-3616

Du Pont Company (Singapore) Pte Ltd
1 HarbourFront Place, #11-01
HarbourFront Tower One,
Singapore 098633
Tel. +65-6586-3022

Europe, Middle East & Africa

Du Pont (U.K.) Limited
Coldharbour Lane
Bristol BS16 1QD
U.K.
Tel. +44-117-931-3191

DuPont China Holding Co. Ltd
Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,
Pudong New District, Shanghai 201203
China
Tel. +86-21-6386-6366 ext.2202

<http://mcm.dupont.com>
<http://photovoltaics.dupont.com>

Asia

DuPont Kabushiki Kaisha
MCM Technical Lab
DuPont Electronics Center
KSP R&D B213
2-1, Sakado 3-chom, Takatsu-ku,
Kawasaki-shi, Kanagawa, 213-0012
Japan
Tel +81 44 820 7575

DuPont Korea Inc.
3-5th Floor, Asia tower #726,
Yeoksam-dong, Gangnam-gu
Seoul 135-719, Korea
Tel. +82-10-6385-5399

E. I. DuPont India Private Limited
7th Floor, Tower C, DLF Cyber Greens,
Sector-25A, DLF City, Phase-III,
Gurgaon 122 002 Haryana, India
Tel. +91-124-4091818